

Designations and standards

Standard	Material designation
Material No.	2.4420
DIN designation	NiFe 44
DIN standard	17745 EN 60404-8-6 : E2
UNS	

Chemical composition (weight - %) acc. to DIN 17745

	Ni	Cr	Fe	C	Mn	Si	Cu	Mo	Al	Others
Min.	bal.	-	42,0				-	-		-
Max.		-	46,0	0.05	0.5	0.3	-	-	0.005	-

Mechanical values (N/mm², %)

	R _{p 0.2}	R _m	A ₅₀	HV
50% cold worked	-	-	-	-
Deep-drawing	-	-	-	-

Magnetic properties

Quality class	Permeability (min.)		Coercivity
	μ ₄	μ _{max}	
MG 40	40.000	100.000	2
MD 60	60.000	130.000	1.2

Saturation induction (T)	Curie temperature (°C)	Saturation magnetostriction (10 ⁻⁶)
1.5	530	+25

Strip thickness 0.1 mm

Physical properties at room temperature

Density	(g/cm ³)	8.3				
Specific heat	(J/kgK)	500				
Thermal conductivity	(W/mK)	16.5				
Resistivity	(Ωmm ² /m)	0.45				
Modulus of electricity	(kN/mm ²)	-				
Expansion coefficient from 20°C to		100	200	300	400	500
	(10 ⁻⁶ /K)	10.6	10.6	10.7	10.7	10.8

Processing

Melting point	(°C)	1.445
Formability		good
Weldability		-

Material characteristics

High permeability, high saturation induction.

Typical applications

Transducers, transformer, residual current circuit breakers, toroidal strip wound cores for special applications

Legal notice

26.03.2019

Publisher

VDM Metals International GmbH
Plettenberger Straße 2
58791 Werdohl
Germany

Disclaimer

All information contained in this document is based on the results of research and development work carried out by VDM Metals International GmbH and the data contained in the specifications and standards listed available at the time of printing. The information does not represent a guarantee of specific properties. VDM Metals reserves the right to change information without notice. All information contained in this document is compiled to the best of our knowledge and is provided without liability. Deliveries and services are subject exclusively to the relevant contractual conditions and the General Terms and Conditions issued by VDM Metals. Use of the most up-to-date version of this document is the responsibility of the customer.

VDM Metals International GmbH

Plettenberger Straße 2
58791 Werdohl
Germany

Phone +49 (0)2392 55 0
vdm@vdm-metals.com
www.vdm-metals.com