

VDM® Alloy HT 80

Designations and standards

Standard	Material designation
Werkstoffnummer	2.4869
DIN Kurzzeichen	NiCr 80 20
DIN	17470 (heating element) 17471 (resistance alloy) 17742, 17753 (wire)
UNS	N06003
ASTM	B 344
SAE AMS	5682

Chemical composition (weight-%) acc. to ASTM B 344

	Fe	Cr	Ni	C	Mn	Si	Cu	Mo	Al	Others
Min.		19	Bal.			0,75				
Max.	1	21		0,15	1,0	1,75	-	-	-	0,01

Mechanical properties at room temperature acc. to DIN 17470 and 17471

	N/mm ²	ksi
Tensile strength (Rm)	≥ 650	≥ 94,3

mm	Wire diameter	Elongation A _{L-100} (in %)
	inches	
0.063 – 0.125	0.025 – 0.049	≈ 14
> 0.125 – 0.5	> 0.049 – 0.197	≈ 18
> 0.5 – 1.0	> 0.197 – 0.394	≥ 18
> 1.0	> 0.394	≥ 25

Creep properties (N/mm²)

Temperature in °C	°F	R _{p 1,0/10³h}
600	1,112	80
700	1,292	40
800	1,472	15
900	1,652	9
1,000	1,832	4
1,200	2,192	0,5

Physical properties at room temperature

Density	(g/cm ³)	8,3
Thermal conductivity	(W/m • K)	14,6
Modulus of elasticity	(kN/mm ²)	200

Temperature in °C °F	Electrical resistivity		Coefficient of thermal expansion (10 ⁻⁶ /K)	Specific heat (J/kg • K)	
	(μΩcm)				
	DIN 17470	ASTM B 344			
20	68	112	108	-	420
200	392	113	110	14,0	-
400	752	115	114	15,0	-
500	932	116	116	15,4	-
600	1,112	115	115	15,5	-
800	1,192	114	114	16	-
1.000	1,832	115	115	17	500
1.200	2,192	117	117	-	-

Processing

Melting point	(°C)	1,400
Max. operating temperature in air	(°C)	1,200 (as heating element) 600 (as resistance alloy)
Formability		good
Weldability		satisfactory
Filler metal		matching

Material characteristics

- High-temperature strength
- Good resistance to oxide scaling and to thermal fatigue up to 1,200 °C (2,192 °F)
- Very stable electrical properties

Typical applications

- Precision resistors
- Multipliers and load resistors
- Potentiometers

Imprint

17.12.2019

Publisher

VDM Metals International GmbH
Plettenberger Straße 2
58791 Werdohl
Germany

Disclaimer

All information contained in this document is based on the results of research and development work carried out by VDM Metals International GmbH and the data contained in the specifications and standards listed available at the time of printing. The information does not represent a guarantee of specific properties. VDM Metals reserves the right to change information without notice. All information contained in this document is compiled to the best of our knowledge and is provided without liability. Deliveries and services are subject exclusively to the relevant contractual conditions and the General Terms and Conditions issued by VDM Metals. Use of the most up-to-date version of this document is the responsibility of the customer.